



BERGQUIST® LIQUI FORM TLF LF3500AB

June 2025

PRODUCT DESCRIPTION

BERGQUIST® LIQUI FORM TLF LF3500AB provides the following product characteristics:

Technology	Silicone
Appearance	Black
Product benefits	- Thermal conductivity: 3.5 W/m-k - Dispensable pre-cured gel - Stable viscosity in storage and in applications - Excellent chemical stability and mechanical stability
Cure	Pre-cured gel
Operating temperature, °C	60 to 200
Application	Thermal management TIM (Thermal interface material)
Typical application	- Handheld devices - Bare die to heat spreader lid - Filling various gaps between heat-generating devices to heatsink - Devices requiring low assembly pressure - High value assemblies with rework - BGA, PGA, PPGA
Flammability rating	UL 94V-0

BERGQUIST® LIQUI FORM TLF LF3500AB is a high conductivity gel thermal interface material designed for demanding applications that require a balance between dispensability and low component stress during assembly and also in the application.

BERGQUIST® LIQUI FORM TLF LF3500AB is a one-part, highly conformable gel with thixotropic properties. The material is precured and requires no curing, mixing or refrigeration. Its unique formulation assures excellent thermal performance, low applied stress and reliable long-term performance.

BERGQUIST® LIQUI FORM TLF LF3500AB is thixotropic and has a natural tack ensuring it forms around the component and stays in place in the application.

TYPICAL PROPERTIES

Physical properties

Density, g/cc	3.1
Viscosity @ 25°C, Pa*sec.	
Low shear rate, 100 s ⁻¹ , Capillary rheometer	300
High shear rate, 1 s ⁻¹ , Parallel plate rheometer	1500
Shelf life, @25°C, days	365

Outgassing properties

Total mass loss, ASTM 595, %	0.21
------------------------------	------

Electrical properties

Volume resistivity, ASTM D257, Ohm-m	10 ¹¹
Dielectric strength, ASTM D149, kV/mm	10
Dielectric constant, ASTM D150, @1 kHz	8.1
Flammability rating, UL rating	94V-0

Thermal properties

Thermal conductivity, ASTM D5470, W/m-K	3.5
---	-----

GENERAL INFORMATION
For safe handling information on this product, consult the Safety Data Sheet (SDS).

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

Not for product specifications
The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on the specifications of this product.

Thawing
1. If refrigerated, allow container to reach room temperature before use.
2. DO NOT open the container before contents reach 25°C temperature. Any moisture that collects on the thawed container should be removed prior to opening the container.

Storage
Store product in an unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal storage: 25°C
Material removed from the package may be contaminated during use. Do not return product to the original package. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.



Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1